



HiCal Stone Grade B (#10 X 200 Mesh) Pulverized

Typical Properties:

<u>Chemical</u>	<u>Average (%)</u>
Loss on Ignition (LOI)	43.8
Moisture	0.01
Total Sulfur (S)	0.047
Calcium as Calcium Oxide (CaO)	55.1
Calcium as Calcium Carbonate (CaCO ₃)	98.3
Magnesium as Magnesium Oxide (MgO)	0.49
Magnesium as Magnesium Carbonate (MgCO ₃)	1.03
Silica (SiO ₂)	0.38
Ferric Oxide (Fe ₂ O ₃)	0.06
Alumina (Al ₂ O ₃)	0.06

Typical Properties:

<u>Physical</u>	<u>Average (%)</u>
Sizing at point of loading	
- Passing 10 Mesh	98.4
- Passing 20 Mesh	61.1
- Passing 60 Mesh	12.5
- Passing 100 Mesh	3.8
- Passing 200 Mesh	3.3
- Passing 325 Mesh	1.7
Loose Bulk Density (#/ft ³) *	90



Packed Bulk Density (#/ft³) *

100

* Not routinely analyzed

Product is registered to NSF60, Drinking Water Treatment Chemicals.